

551, 682

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
14 October 2004 (14.10.2004)

PCT

(10) International Publication Number
WO 2004/087807 A1

(51) International Patent Classification⁷: **C08L 23/12**,
C08F 10/06, 210/16, 210/06, 2/00

(21) International Application Number:
PCT/EP2004/003307

(22) International Filing Date: 29 March 2004 (29.03.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
03007669.9 3 April 2003 (03.04.2003) EP

(71) Applicant (for all designated States except US): **BASELL
POLIOLEFINE ITALIA S.P.A.** [IT/IT]; Via Pergolesi,
25, I-20124 Milano (IT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **NEWS, Jean**
[US/IT]; Via Ripagrande, 63, I-44100 Ferrara (IT).
MASSARI, Paola [IT/IT]; Via E. Farolfi, 3, I-44100
Ferrara (IT). **ZIMMERMANN, Hans-Jürgen** [DE/DE];
Freiligrathstrasse 9, 65719 Hofheim am Taunus (DE).

(74) Agent: **GAVERINI, Gaetano**; Basell Poliolefine Italia
S.p.A., Intellectual Property, Via Pergolesi, 25, I-20124 Mi-
lano (IT).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,
GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

Declarations under Rule 4.17:

- as to applicant's entitlement to apply for and be granted a
patent (Rule 4.17(ii)) for all designations
- of inventorship (Rule 4.17(iv)) for US only

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: **IMPACT RESISTANT POLYOLEFIN COMPOSITIONS**

(57) Abstract: Olefin polymer composition comprising (by weight, unless otherwise specified): A) 60 - 95% of a propylene homopolymer or copolymer having a Polydispersity Index (P.I.) value of from 4.6 to 10 and a content of isotactic pentads (mmmm), measured by ¹³C NMR on the fraction insoluble in xylene at 25 °C, higher than 98 molar; B) 5 - 40% of a copolymer of ethylene containing from 40% to 70% of propylene or C₄-C₁₀ α-olefins) or of combinations thereof, and optionally minor proportions of a diene; said composition having a Temperature Rising Elution Fractionation (TREF) profile, obtained by fractionation in xylene and collection of fractions at temperatures of 40 °C, 80 °C and 90 °C, in which the ethylene content Y of the fraction collected at 90 °C satisfies the following relation (I): $Y \leq -0.8 + 0.035X + 0.0091X_2$ wherein X is the ethylene content of the fraction collected at 40 °C and both X and Y are expressed in percent by weight, and a value of intrinsic viscosity [η] of the fraction soluble in xylene at 25 °C of from 1.8 to 4.2 dl/g.

WO 2004/087807 A1